

Dr. Fixit Powder Waterproof



INTEGRAL POWDER WATERPROOFING COMPOUND FOR PLASTER & CONCRETE

Description

Dr. Fixit Powder Waterproof is composed of waterproofing additives, dispersed in inert fine filler. It is an integral powder-waterproofing admixture used for waterproofing of concrete and cement plasters, because It makes concrete cohesive & reduces porosity & improve water tightness .

Standard compliances / Specification

- Meets the requirements of IS : 2645 - 75 standard

Areas of Application

- Basements,
- Roof slabs and screeds,
- Water retaining structures,
- External plastering,
- Bathrooms
- Balconies.

Features & Benefits

- **Corrosion** - Chloride-free hence no chances of corrosion of reinforcement bars.
- **Water seepage** - As an effective pore filler, helps to fill capillaries and pores to prevent water seepage.
- **Consistency** - Makes the mix cohesive and denser, hence the concrete & plaster has reduced permeability .
- **Economics** - Most economical water proofing additive, reduces water absorption.
- **Setting & strength** - Does not affect the setting time and strength. Of the cured concrete.
- **Compatibility** - Compatible with all types & grades of cements.

Method of Application

1 HAND MIXING

- Add Dr. Fixit Powder Waterproof to the dry mix of cement sand and mix evenly with a spade, until an even mix is obtained.
- Add the measured quantity of potable water as per decided W/C ratio and mix to a homogeneous & uniform consistency concrete / mortars.
- Place the mixed concrete / mortar into shuttering, provided
- Cure the concrete / mortar surface as per regular practices of water curing.

2 MACHINE MIXING

- Charge the Cement & sand as per the mix design into concrete mixer & mix for one minute. Add 500 g of Dr. Fixit Powder Waterproof for every 50 kg bag of cement. & mix for one minute.
- Add the measured quantity of potable water as per W/C ratio and mix for 2-3 minutes to a lumps free homogeneous concrete.
- Place the mixed concrete mortar into shuttering provided.
- Cure the concrete / mortar surface as per regular practices of water curing.

Dr. Fixit Powder Waterproof



INTEGRAL POWDER WATERPROOFING COMPOUND FOR PLASTER & CONCRETE

Precautions & Limitations

- Do not add Dr. Fixit Powder Waterproof directly to water.
- Do not add Dr Fixit Powder Waterproof in wet concrete/ mortar.

Technical Information

PROPERTIES	SPECIFICATION	RESULTS
Appearance		Free flowing powder
Colour		Off white
Bulk density- tapped, gm/ml		0.8 ± 0.05
Setting time @ 30°C, mins	IS : 2645	30 - 600
Compressive strength, N/MM ²	IS : 2645	Matches to control mix
Water permeability	IS : 2645	35% of control mix

Dosage

- 500 gms of Dr Fixit Powder Waterproof for 50 kgs bag of cement.

Packaging

- 500 g

Shelf Life & Storage

- Shelf life is 12 months from date of manufacturing in unopened containers.
- Store at cool & dry place, away from sun heat & fire.

Health & Safety Precautions

- Use rubber hand gloves & safety goggles, while using Dr Fixit Powder Waterproof.
- In case of contact with skin, wash with plenty of water.
- Keep out of reach of children's.

Dr. Fixit Powder Waterproof



INTEGRAL POWDER WATERPROOFING COMPOUND FOR PLASTER & CONCRETE

Other Product Categories Available

DR. FIXIT has wide range of Waterproofing & Construction chemicals which includes,

- Waterproofing Products
- Repair Products
- Sealants
- Flooring Products
- Exterior Coating Products
- Tile Fixing Range
- Concrete Admixtures
- Grouts



Pidilite Industries Limited

Construction Chemicals Division
Ramkrishna Mandir Road
Post Box No. 17411
Andheri (E) Mumbai 400059 INDIA
Tel +91-22-2835 7000 • Fax +91-22-2835 7008
website www.doctor-fixit.com • E-mail drfixit@pidilite.com
Toll Free No.: 1800-22-5502

DISCLAIMER The product information & application details given by the company & its agents has been provided in good faith & meant to serve only as a general guideline during usage. Users are advised to carry out tests & take trials to ensure on the suitability of products meeting their requirement prior to full scale usage of our products. Since the correct identification of the problems, quality of other materials used and the on-site workmanship are factors beyond our control, there are no expressed or implied guarantee / warranty as to the results obtained. The company does not assume any liability or consequential damage for unsatisfactory results, arising from the use of our products.