

Nitotile MPA

Multipurpose tile adhesive for exterior, tile-on-tile, tile-on-glass and specialised applications

Uses

Nitotile MPA tile adhesive is a high quality adhesive used for the permanent fixing of tiles over smooth surfaces such as existing tiles, ceramic tiles or glass, subjected to damp and tropical conditions and for specialised applications such as tile on tile, tile-on-glass and glass mosaic tiles.

Advantages

- Polymer modified - prewetting of tiles not required and hence less prone to cracking of mortar
- Single component - ease of application
- Non toxic - User friendly application
- Excellent adhesion on smooth surfaces - Develops high adhesive bond strength
- Non shrink - excellent bond with the substrate
- Excellent work and open wet time of 2 hrs at 30°C - allows the mason to fix tiles at ease even under hot conditions
- Self cure - does not require external curing
- Forms a dense and impermeable mortar bed - waterproof

Standard compliance

Nitotile MPA confirms to IS 15477 Type I & II.

Description

Nitotile MPA is a single component, polymer modified cement based product available in Grey and White colours.

Technical support

The company provides a technical advisory service supported by a team of specialists in the field.

Properties

Density of the mixed material	: 1.95g/cc	
Pot life	: Approx. 2 hrs	
Setting time	: Initial - 13 hrs Final - 24 hrs	
Pull out bond strength on tile at 28 days	: > 1 N/mm ²	
Compressive strength (N/mm ²)	: 3 days	10.4
	: 7 days	16.0
	: 28 days	21.6
W/P ratio	: 0.25	

Application instructions

Surface preparation

All surfaces must be sound and thoroughly cleaned before Nitotile MPA is applied. All traces of grease or oil must be removed with suitable degreaser. All loose particles of mortar, old wallpaper, paint etc., must be physically removed. In case of cementitious surfaces, the areas of application must be thoroughly wetted with water to obtain saturated surface dry condition.

Incase of smooth surfaces , prewetting of substrate with water is not essential.

Mixing

Nitotile MPA should be mixed with water in the ratio of 3 : 1 by volume or 4:1 by weight. While mixing, add powder to the water to avoid lump formation. A slow speed drill fitted with a suitable mixing paddle is recommended for mixing. Hand mixing may also be resorted to if small quantities are mixed. (Note : Use of chilled water in extreme temperatures will increase open time of Nitotile MPA).

Application

Nitotile MPA , is spread on the substrate to a uniform thickness of 2 - 3mm. This is then combed horizontally with a notched trowel. The tiles are then placed firmly into the adhesive bed ensuring good contact with the mortar by a twisting motion.

Finishing

The excess material shall be removed with a damp cloth before it sets.

Joint grouting with Nitotile Grout may be commenced 24 hours after tiles have been fixed.

Estimating

Packaging

Nitotile MPA is supplied in 30 kg bags.

Coverage

Approximately 3.8 kg of Nitotile MPA is required per sq.m when uniformly applied at 2mm thickness. Material consumption will increase if the substrate is not even.

Nitotile MPA

Storage

Shelf life

12 months in unopened bags under normal warehouse conditions.

Nitotile MPA must be stored in a cool dry place.

Precautions

Health & Safety instructions

Nitotile MPA is cement based and hence alkaline in nature. Care should be taken to avoid inhalation of dust and contact with skin and eyes during use.

Additional information

The Fosroc range of associated products include high strength cementitious and epoxy grout, polyester resin based mortar for rapid presetting of steel shims to level or for direct bedding of small base plates. Also available a range of products for use in construction; viz., admixtures, curing compounds, release agents, flooring systems, repair mortars, sealants and water-proofing compounds.

Separate datasheets are available on these products.



Fosroc Chemicals (India) Pvt. Ltd.

Head Office

"Sapthagiri Palace", No.38,
II & III Floor, 12th Cross,
CBI Road, Ganganagar North,
Bangalore 560 024

Important note :

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation specification or information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products whether or not in accordance with any advice, specification, recommendation or information given by it.

telephone

++91 80-42521900

fax

++91 80-23551510

e-mail

enquiryindia@fosroc.com

Regional Offices

Chennai

No. 26(old no.33), 1st Floor,
1st Street Postal Colony,
West Mambalam,
Chennai 600 033.
Ph: +91 44 24899949-94
Fax: 044-24896641

Mumbai

MBC Park, 12th floor, Office No.12B,
'D' Block, Near G Corp/Hyper City
Kasarwadawali, Ghodbunder Road,
Thane (West) 400 615
Ph: +91 22 6229 6800
Fax: 022 62296809

Noida

Unit No. 601, Highway Tower-II
A-13/2, 6th Floor, Sector- 62
Gautam Buddha Nagar,
Noida 201 309, Uttar Pradesh
Ph: +91 120 6121900

Kolkata

304, Jodhpur Park
Kolkata 700 068
Ph: +91 33-65343188
Fax: 033-2499-0280