

ReArm Coat ZP

(Formerly known as MYK COAT ZP)

Epoxy Zinc Rich Primer



TECHNICAL DATA SHEET

Product Description

ReArm Coat ZP is a two component anticorrosion primer for reinforced steel in concrete repairs. It actively resists corrosion within the confines of the repair location.

Uses

- Used as a primer on reinforced bars for anticorrosive system and in concrete repairs
- Also can be used on exterior surfaces as a coating of machinery, fertilizers tanks, and girders in industries.

Features and Benefits

- Zinc rich system combats corrosion
- Permanent protection to the steel structure
- Excellent adhesion to steel
- Time Saving-touch dry after 35 to 40 Minutes
- Exhibits excellent bond strength in cementitious repair

Application Method

Mixing & Application:

Stir the Hardener and Resin individually with drill mixer of proper size. Then add the entire content of the hardener into Resin container and stir the two components thoroughly using a low speed mixer for about 2 to 3 Minutes until a uniform color of the mixture is obtained. Corroded steel shall be fully exposed and all loose scale and corrosion deposits shall be removed. Then apply ReArm Coat ZP as soon as possible over the dry steel surface after completion of the preparation work by using brush.



ReArm Coat ZP

(Formerly known as MYK Coat ZP)

Epoxy Zinc Rich Primer



TECHNICAL DATA SHEET

Consumption

6.5 m² per Kg @ 50 microns .

Packaging

- 0.8 Kg Pack

Storage and Shelf Life

Store in cool dry place

Shelf Life: 24 months from date of manufacturing.

Health & Safety

Use of hand gloves is necessary while mixing the product in case of contact with skin or eyes, use plenty of water to wash and obtain medical helps immediately.

Product Categories Available



Legal Note

The information, and, in particular, the recommendations relating to the application and end-use of MYK Arment products, are given in good faith based on MYK Arment current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with MYK Arment's recommendations. In practice, the difference in materials, substrates and actual site conditions are such that no warranty in respect of merchant ability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. the user of the product must test the product's suitability for the intended application & purpose. MYK Arment reserves the right to change the properties of its products. the proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local product data sheet for the product concerned, copies of which will be supplied on request.