

PRODUCT CODE 5429

Tile Grout - Cement Based

Asian Paints SmartCare Tile Grout - Cement Based is a single component polymer modified tile grout for filling tile joints up to 5 mm width. It is a specially formulated premium, fast setting, low shrinkage grout that prevents ingress of water through the joint.



PRODUCT BENEFITS

Specification

Meets the requirements of ANSI 118.6 (Specification for tile grouts)

Easy to mix

Cement based easy to mix joint filler available in 7 brilliant shades

Impermeability

Water repelling impermeable joint filler suited for domestic and commercial floors, walls etc.

Excellent adhesion


Sustainable and durable for a long time

Easy to clean

Non-dusting and easy to clean

PRODUCT FEATURES

AVAILABLE PACKS



Shelf life: 12 months from the date of manufacture when stored in original packaging under normal dry conditions.

COVERAGE

Tile Dimension, mm			Consumption, Kg/mtr ² Tile Joint of width		
LENGTH	WIDTH	THICKNESS	3 mm	4 mm	5 mm
300	300	8	0.32	0.42	0.53
300	300	10	0.39	0.53	0.66
300	300	20	0.80	1.06	1.33
300	600	10	0.30	0.40	0.50
330	330	10	0.36	0.48	0.60
450	450	12	0.32	0.42	0.53
600	600	12	0.24	0.32	0.40
200	300	6	0.29	0.39	0.49

COLOURS AVAILABLE

7 Shades*



*Available in 7 brilliant shades

RECOMMENDED USAGE



HOW TO APPLY

APPLICATION PROCESS

APPLICATION	PROCEDURE	APPLICATION	PROCEDURE
STEP 1	Before grouting make sure that the tiles are firmly set and adhesive is cured.	STEP 5	Apply the material within 30 minutes of mixing.
STEP 2	Tile joints must be clean & free of oil or any other foreign matter and about 2/3 rd of the depth of tile should be available for grouting.	STEP 6	Remove excessive grout without disturbing the compactness of the applied material.
STEP 3	Add 1 Kg tile grout to about 300 to 350 ml of potable water & mix till it is free from lumps.	STEP 7	Allow to harden for 2-3 hours and then remove excess material with damp (and Not Wet) sponge.
STEP 4	Dampen the surface. Spread the grout using rubber grout float ensuring that no air gaps are left in the joint.	STEP 8	Allow the joint to cure for 24 hrs before subjecting it to normal service conditions. In case of exterior joints, protect from direct sunlight/ rains for at least 24 hours.

ADDITIONAL INFORMATION**PRECAUTIONS**

- › Do not use when high chemical, impact, stain resistance, is required or in industrial environment. In such cases, use Asian Paints Epoxy tile grout.
- › The actual shade may not match 100 % with that in shade card. Shade card is for indication purpose.
- › When 2 or more bags are required, it is advisable to dry blend the powders first to avoid color variation.

SAFETY FEATURES

- › Kindly refer to the MSDS for Asian Paints SmartCare Tile Grout - Cement Based which gives detailed information on safety measures while handling the material.
- › Store the bag tightly closed in a cool, dry place
- › Keep out of reach of children and away from eatables.
- › May be harmful if swallowed. In case of ingestion seek immediate medical attention.
- › Wear eye protection during application. In case of contact with eyes, rinse immediately with plenty of water and if required seek medical advice.
- › It is recommended to wear suitable nose pad during surface preparation, mixing, application to avoid dust inhalation.

TECHNICAL DETAILS

a. Form: Free flowing powder

b. Color: As per shade

c. Mix density: 1.75 - 2.05 (depending on shade)

d. Pot Life: 1 Hour

e. Curing time: 24 Hours

f. Cleaning tools: with water immediately after use